

DATE SUBMITTED: 02-JUNE-2015
DATE ISSUED: 12-JUNE-2015
REPORT NO: 31961
COMPANY ORDER NUMBER: Not Stated

CUSTOMER CONTACT NAME: SUSANNE DAMMERS
EMAIL: service@mah.de
TEL: +49-89-74 48 24 82
FAX: +49-89-74 48 24 83

COMPANY: MUNCHNER AUTOSTOFF HANDEL GMBH
ISARSTR 1
D-82065
BAIERBRUNN/BUCHENHAIN
GERMANY

CUSTOMER SAMPLE DESCRIPTION

FIBRE COMPOSITION:	Not Stated
SAMPLE QUALITY/COLOUR:	207x, 208x, 217x, 218x Teal Fabric
STOCK BATCH / REF NUMBER:	Not Stated
SAMPLE DESCRIPTON:	PVC Fabric
FABRIC CUSTOMER:	Not Stated
FABRIC SUPPLIER:	Not Stated

FIRE TEST REQUESTED:

(Confidential Report)

BS 7176: 2007+ A1:2011 Predictive Test for Low Hazard: Resistance to Ignition of Upholstered Furniture for Non-Domestic Seating by Testing Composites. Tested in accordance with BS EN 1021-1: 2014 Resistance to ignition source: smouldering cigarette & BS EN 1021-2: 2014 Resistance to ignition source: match flame equivalent.

LAUNDERING PROCEDURE:

The sample was subjected to the water soaking procedure @ 40±1°C as stated in BS EN 1021-1 & 2 Annex D.

CONDITIONING PROIR TO TESTING:

The sample was conditioned immediately before the test for @ least 72 h in indoor ambient conditions and then for @ least 16 h at 23 +/- 2 °C and 50 +/- 5 % r h

Authorised signature:

Signed: v

Zeb Alam
Technical Manager

TEST CERTIFICATE

DATE SUBMITTED: 02-JUNE-2015
DATE ISSUED: 12-JUNE-2015
REPORT NO: 31961
COMPANY ORDER NUMBER: Not Stated

UPHOLSTERY FILLING SOURCE 0 & 1:

GRADE: CMHR35
APPROX DENSITY: 35 kg per m³
APPROX HARDNESS RANGE: 130 N

SIZE OF TEST RIG:

BACK JUNCTION: 450+/-2 mm x 300+/-2 mm
SEAT JUNCTION: 450+/-2 mm x 150+/-2 mm

PROCEDURE:

The sample was mounted over the foam described above using the test rig as specified in BS EN 1021-1 & 2 Clause 6 Apparatus.

TESTING ENCLOSURE AND ATMOSPHERE:

The sample was tested in an atmosphere with a temperature of 10 °C to 30°C and a relative humidity of 15% to 80%. The sample was tested in an enclosure with a volume greater than 20m³

REQUIREMENTS:

Ignition Source: Cigarette
Progressive Smouldering (detected within duration): 60 minutes after ignition of cigarette
Flaming (detected within duration): 60 minutes after ignition of cigarette

Ignition Source: Match flame (15±1 second application time)
Progressive Smouldering (maximum duration): 120 seconds after ignition of burner
Smoking (maximum duration): 120 seconds after ignition of burner
Flaming (maximum duration): 120 seconds after ignition of burner
Afterglow (maximum duration): 120 seconds after ignition of burner

DATE OF TEST: 11-June-2015

Fire test carried out by: Zeb Alam

RESULTS: The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Observation of test:

Ignition Sources	Position	Duration of		Special Features of Burning		Extent of damage to component			
						Vertical (mm)		Horizontal (mm)	
		Flames (minutes)	Smouldering (minutes)	Charring	Melting	Length	Width	Length	Width
Test 1: Source 0	LHS	00.00	Failed to smoulder	Yes	Yes	N/A	N/A	N/A	N/A
Test 2: Source 0	RHS	00.00	Failed to smoulder	Yes	Yes	N/A	N/A	N/A	N/A
Test 3: Source 0	RHS	00.00	Failed to smoulder	Yes	Yes	N/A	N/A	N/A	N/A
Test 1: Source 1	LHS	00.00	00.00	Yes	Yes	100	27	24	21
Test 2: Source 1	RHS	00.00	00.00	Yes	Yes	94	25	22	20
Test 3: Source 1	LHS	00.00	00.00	Yes	Yes	103	25	24	23

LHS=Left Hand Side M= Middle RHS= Right Hand Side

COMMENTS & OBSERVATIONS:

The sample tested **complies** with the requirements of BS 7176: 2007+ A1:2011 Predictive Test for Low Hazard: Resistance to Ignition of Upholstered Furniture for Non-Domestic Seating by Testing Composites (not recommended for use in higher hazard areas).

Smouldering Cigarette Test: **PASS (P0)**

Match Flame Equivalent Test: **PASS (P1)**

Please note: this test results issued on this certificate refer only to the item tested and therefore doesn't relate to the lot or batch of the product / sample. This test certificate shall not be duplicated.

Page 2 of 2

48B Halliwell Business Park, Rossini Street, Bolton, BL1 8DL

T: 01204 840086 F: 01204 840524 E: zeb@ifs-labs.com