

Our Ref: SW/PN/GL

7 September 2013

Report 206869/10/2

Page 1 of 3

Oniro bv
Postbus 180
3700 AD Zeist
The Netherlands

DATE RECEIVED	:	29 AUGUST 2013
QUALITY/REFERENCE	:	NITROXX ULTRA
REPUTED FIBRE CONTENT	:	NOT GIVEN
FABRIC DESCRIPTION	:	WOVEN
COLOUR/DESIGN	:	DARK BROWN

REQUEST: BSEN1021-1: 2006 (smouldering cigarette);
BSEN1021-2: 2006 (Match flame equivalent)

COMMENTS: The sample tested meets the flammability performance requirements of
BS EN 1021-1:2006 and BS EN 1021-2:2006



S. WISEMAN
LABORATORY MANAGER



P. NEESAM
HEAD OF FLAMMABILITY

This report shall not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.



Our Ref: SW/PN/GL

7 September 2013

Report 206869/10/2

Page 2 of 3

**BS EN 1021-1/2:2006 Furniture - Assessment of the ignitability of upholstered furniture –
Part 1 Ignition Source: Smouldering cigarette.
Part 2 Ignition Source Match flame equivalent.**

Conditioning

Immediately prior to testing the sample of fabric, Ref: Ultraxx was subjected the water soaking procedure described in Annex D, and then dried at indoor ambient conditions. It was then subjected to 24 hours in specified conditions, having a temperature of $(23 \pm 2^\circ\text{C})$ and relative humidity of $(50 \pm 5\%)$.

Procedure

The specimens were mounted over fillings of non-flame-retardent polyurethane foam with a density of approximately $20\text{--}22 \text{ kg/m}^3$.

Results

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

<u>Ignition Source</u>	<u>Ignitability Performance</u>
0	NI (Non-ignition)
0	NI (Non-ignition)
1	NI (Non-ignition)
1	NI (Non-ignition)
1	NI (Non-ignition)

Our Ref: SW/PN/GL

7 September 2013

Report 206869/10/2

Page 3 of 3

	Cigarette		Match-equivalent flame		
	1	2	1	2	3
<u>Smouldering Criteria</u> (Yes/No)					
Unsafe escalating combustion	No	No	No	No	No
Test assembly consumed	No	No	No	No	No
Smoulders to extremities	No	No	No	No	No
Smoulders through thickness	No	No	No	No	No
Smoulders more than 1 hour	No	No	No	No	No
More than 100mm from source	No	No	No	No	No
<u>Flaming Criteria</u> (Yes/No)					
Duration of flames (s)	/	/	2	1	1
Unsafe escalating combustion	No	No	No	No	No
Test assembly consumed	No	No	No	No	No
Flames to extremities	No	No	No	No	No
Flames through thickness	No	No	No	No	No

Comments

The sample tested meets the flammability performance requirements of BS EN 1021-1:2006 and BS EN 1021-2:2006